VINAWOOD CO., LTD
Sales Office: +84-83-333-2333
Email: plywood@vinawoodltd.com



TOP FORM - FILM FACED PLYWOOD

SKU: FFP0600

Top Form is surfaced with optional double coating 220 gsm, Vinawood Top Form will sustain your strictest requirements.

WHY TOP FORM?

Top Form is a product of superior quality proudly made in Vietnam. For customers that are used to Russian Birch Plywood, Top Form is a perfect alternative due to its equivalent density to Birch. Made with highest quality materials, Vinawood Top Form Film Faced Plywood will satisfy the strictest requirements for formwork panels.

WHAT IS FILM FACED PLYWOOD?

Film Faced Plywood is made from plywood that is strengthened with cross-wise structure. Film Faced Plywood is often used for formwork and shuttering purposes. Coated with 100% phenolic film, Film Faced Plywood will withstand many repetitions of concrete pouring while sustaining smooth concrete quality.

WHAT IS IMPORTANT IN CHOOSING FILM FACED PLYWOOD?

Key decision factors of Film Faced Plywood are its species, film coating, and repetition. These factors will determine how durable the panels will be, and the concrete surface they produce.

WHY VINAWOOD?

VINAWOOD is a mill in Vietnam with well-known reputation of over 30 years. VINAWOOD is also familiar with many standards and timber regulations that will make your journey consuming these panels easier. Over the past year, VINAWOOD maintains 99% satisfaction rates. It is also familiar with multi-modal shipping that will deliver Vietnam plywood to you fast, cheap, and safe. VINAWOOD is supplier of Top 5 Formwork companies in the world.

ADDITIONAL INFORMATION

Listed product attributes are for reference only.
Contact us for product customization and best price offer today!

VINAWOOD CO., LTD
Sales Office: +84-83-333-2333
Email: plywood@vinawoodltd.com

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – Top grade 220 gsm
	Back	Phenolic Surface Film – Top grade 220 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	35
Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	650
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	5000 | 6000 | 8000 | 9000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Min Bending Strength (Along Grain) (Mpa)	50 | 60 | 35 | 45
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP06002440122012 | FFP06002440122015 | FFP06002440122018 | FFP06002440122021 | FFP06002500125012 | FFP06002500125015 | FFP06002500125018 | FFP06002500125021
	Place of Origin	Vietnam

Listed product attributes are for reference only.
Contact us for product customization and best price offer today!