
VINAWOOD

#1 PLYWOOD SUPPLIER IN VIETNAM

PRODUCT E-CATALOG



Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



TABLE OF CONTENTS

Commercial Plywood 2
Film Faced Plywood 7
HDO Plywood 26
KS Tego 35
Laminated Veneer Lumber (LVL) 39
Marine Plywood 42
MDO Plywood 46
Product Sample 55

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



COMMERCIAL PLYWOOD

Commercial Plywood is a plywood with veneer face/back made for different purposes such as packing, furniture, and flooring etc.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



CONSPLY COMMERCIAL PLYWOOD

SKU: CP0400

ConsPly is a type of commercial plywood that uses WBP Melamine Class 2 glue to serve affordable formwork concrete-pouring purposes.

Sizes	Dimensions (mm)	1220×2440 mm
	Thickness (mm)	11 | 11.5 | 12
Materials	Face	Bintangor A | Local A
	Back	Bintangor B | Local B
	Face Color	Natural Wood Color
	Wood Species	Mixed Hardwood
	Core Grade	Mixed Grade
	Glue Type	WBP Melamine Economy
Application	Application	Formwork
	Formaldehyde Emissions	E2
Technical Performance	Width & Length Tolerances (mm)	1.0 per meter
	Moisture Content (%)	12
	Density (kg/m3)	500

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



FPLY BIRCH PLYWOOD

SKU: CP0300

FPly Birch is a plywood panel that is made to look like Russian Birch Plywood from the outside, but rather utilizes tropical hardwood in the core for competitive pricing and lead time.

Sizes	Dimensions (mm)	1220×2440 mm
	Thickness (mm)	12 | 15 | 18 | 21
Materials	Face	Birch
	Back	Birch
	Face Color	Natural Wood Color
	Wood Species	Mixed Hardwood
	Core Grade	Fully-composed AA Grade
	Glue Type	MR Top
Application	Application	Furniture
	Formaldehyde Emissions	Carb P2
Technical Performance	Width & Length Tolerances (mm)	1.0 per meter
	Moisture Content (%)	12
	Density (kg/m3)	605

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



PACKPLY EXTRA COMMERCIAL PLYWOOD

SKU: CP0200

PackPly Extra is two-time hotpress packing plywood with Bintangor or Okume face back. PackPly Extra has stable moisture content and tolerance to serve strict requirements for shipping crate or box making.

Sizes	Dimensions (mm)	1220×2440 mm
	Thickness (mm)	11 | 11.5 | 3 | 5 | 6 | 7 | 8 | 12 | 15 | 18 | 21 | 9
Materials	Face	Bintangor A | Bintangor B | Local A | Local B | Okume A | Okume B
	Back	Bintangor A | Bintangor B | Local A | Local B | Local C | Okume A | Okume B
	Face Color	Natural Wood Color
	Wood Species	Mixed Tropical Wood
	Core Grade	Mixed Grade
	Glue Type	MR Standard
Application	Application	Packing | Padding
	Formaldehyde Emissions	E1 | E2
Technical Performance	Width & Length Tolerances (mm)	1.0 per meter
	Moisture Content (%)	15
	Density (kg/m3)	400

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



PACKPLY COMMERCIAL PLYWOOD

SKU: CP0100

PackPly is the most affordable plywood with one time hot-press for most economical purpose.

Sizes	Dimensions (mm)	1220×2440 mm
	Thickness (mm)	11 | 11.5 | 3 | 5 | 6 | 7 | 8 | 12 | 15 | 18 | 21 | 9
Materials	Face	Bintangor A | Bintangor B | Local A | Local B | Okume A | Okume B
	Back	Bintangor A | Bintangor B | Local A | Local B | Local C | Okume A | Okume B
	Face Color	Natural Wood Color
	Wood Species	Mixed Tropical Wood
	Core Grade	Mixed Grade
	Glue Type	MR Eco
Application	Application	Packing
	Formaldehyde Emissions	E2
Technical Performance	Width & Length Tolerances (mm)	1.0 per meter
	Moisture Content (%)	15
	Density (kg/m3)	400

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



FILM FACED PLYWOOD

Our best-selling category for concrete formwork purposes. Our Film Faced Plywood is one of the most reliable on the market.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



TOP FORM PLUS - FILM FACED PLYWOOD

SKU: FFP06PL

Top Form Plus is a product of superior quality proudly made in Vietnam. For customers that are used to Russian Birch Plywood, Top Form Plus is a perfect alternative due to its equivalent density to Birch. Made with highest quality materials, Vinawood Top Form Plus Film Faced Plywood will satisfy the strictest requirements for formwork panels.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – Top grade 220 gsm
	Back	Phenolic Surface Film – Top grade 220 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade Full sheet
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	50

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	650
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	5000 | 6000 | 8000 | 9000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Min Bending Strength (Along Grain) (Mpa)	50 | 60 | 35 | 45
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP06PL2440122012 | FFP06PL2440122015 | FFP06PL2440122018 | FFP06PL2440122021 | FFP06PL2500125012 | FFP06PL2500125015 | FFP06PL2500125018 | FFP06PL2500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



TOP FORM - FILM FACED PLYWOOD

SKU: FFP0600

Top Form is surfaced with optional double coating 220 gsm, Vinawood Top Form will sustain your strictest requirements.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – Top grade 220 gsm
	Back	Phenolic Surface Film – Top grade 220 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	35

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	650
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	5000 | 6000 | 8000 | 9000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Min Bending Strength (Along Grain) (Mpa)	50 | 60 | 35 | 45
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP06002440122012 | FFP06002440122015 | FFP06002440122018 | FFP06002440122021 | FFP06002500125012 | FFP06002500125015 | FFP06002500125018 | FFP06002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



PRO FORM HIGH DENSITY - FILM FACED PLYWOOD

SKU: FFP05HD

Pro Form High Density takes quality to another level. Vinawood Pro Form High Density Film Faced Plywood is preferred by Top 5 Formwork companies in the world. Made with high density hardwood and phenolic glue, Pro Form High Density is very durable and complies to market requirements in Europe and North America.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – Top grade 125 gsm
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	630
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	5000 | 6000 | 7000 | 9000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 60 | 35
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP05HD2440122012 | FFP05HD2440122015 | FFP05HD2440122018 | FFP05HD2440122021 | FFP05HD2500125012 | FFP05HD2500125015 | FFP05HD2500125018 | FFP05HD2500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



PRO FORM - FILM FACED PLYWOOD

SKU: FFP0500

Vinawood Pro Form Film Faced Plywood is preferred by Top 5 Formwork companies in the world. Made with high quality hardwood and phenolic glue, Pro Form Eco is very durable and complies to market requirements in Europe and North America.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – Top grade 125 gsm
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP05002440122012 | FFP05002440122015 | FFP05002440122018 | FFP05002440122021 | FFP05002500125012 | FFP05002500125015 | FFP05002500125018 | FFP05002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



FORM EXTRA - FILM FACED PLYWOOD

SKU: FFP0400


Form Extra is an upgrade from our most popular product Form Basic. While Form Basic is a well-rounded product, Form Extra takes normality to a higher level. The main difference between Form Extra and Form Basic is a more durable glue for harsh environmental conditions.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – High-gsm Standard 165 gsm
	Back	Phenolic Surface Film – High-gsm Standard 165 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Melamine Top
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	15

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP04002440122012 | FFP04002440122015 | FFP04002440122018 | FFP04002440122021 | FFP04002500125012 | FFP04002500125015 | FFP04002500125018 | FFP04002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



FORM BASIC - FILM FACED PLYWOOD

SKU: FFP0300

Form Basic is our best selling Vietnam Film Faced plywood. It is made from 100% Hardwood, WBP Glue, and Premium Phenolic Coating Surface. This plywood sheet is made and tested with rigorous procedures to ensure quality consistency.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – High-gsm Standard 165 gsm
	Back	Phenolic Surface Film – High-gsm Standard 165 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Melamine Standard
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	10

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP03002440122012 | FFP03002440122015 | FFP03002440122018 | FFP03002440122021 | FFP03002500125012 | FFP03002500125015 | FFP03002500125018 | FFP03002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



ECO FORM - FILM FACED PLYWOOD

SKU: FFP0100

Eco Form is a most effective cost-saving 2-time hotpress Film Faced Plywood on the market. Equipped with 100% Hardwood, this product will outperform any 1-time hotpress poplar plywood in the market. Eco Form Vietnam Film Faced Plywood is a great choice for any project. Our plywood is made from the highest quality materials and is perfect for a variety of applications. Our film faced plywood is sure to meet your needs and exceed your expectations.

Sizes	Dimensions (mm)	1220.00 x 2440.00 mm | 2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – High-gsm Standard 165 gsm
	Back	Phenolic Surface Film – High-gsm Standard 165 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	Mixed Grade
	Glue Type	WBP Melamine Eco
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	6

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1.0 per meter | 1mm per 1 meter
	Thickness Tolerance (mm)	EN315 | According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	550
	Bonding Strength (Mpa)	1 | 1.0
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	50 | 30 | 35 | 45
	Min Bending Strength (Across Grain) (Mpa)	15 | 20 | 25 | 30
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP0100-V001 | FFP01002440122012 | FFP01002440122015 | FFP01002440122018 | FFP01002440122021 | FFP01002500125012 | FFP01002500125015 | FFP01002500125018 | FFP01002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



ECO FORM PLUS - FILM FACED PLYWOOD

SKU: FFP01PL

Eco Form Plus is an upgrade from our most economical product line — Eco Form. Eco Form can be used for approximately 6-8 times which are best for market that requires strict quality while having to maintain most competitive pricing. Eco Form Plus is a sweet spot Vietnam Film faced Plywood product from Vinawood – a renowned Vietnam Plywood Supplier.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – High-gsm Standard 165 gsm
	Back	Phenolic Surface Film – High-gsm Standard 165 gsm
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	Mixed Grade
	Glue Type	WBP Melamine Standard
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	8

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	570
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 5000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	30 | 35 | 45 | 55
	Min Bending Strength (Across Grain) (Mpa)	15 | 20 | 25 | 30
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP01PL2440122012 | FFP01PL2440122015 | FFP01PL2440122018 | FFP01PL2440122021 | FFP01PL2500125012 | FFP01PL2500125015 | FFP01PL2500125018 | FFP01PL2500125021
	Place of Origin	Vietnam



Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



SINGLE FORM - FILM FACED PLYWOOD

SKU: FFP0200

Single Form by VINAWOOD is the cost-effective formwork materials for projects that require fewer usage times and faster construction timeline. One side is coated with waterproofing phenolic layer while the other side is core veneer. This construction reduces cost while maintaining key characteristics of this plywood. The main market for this formwork materials is currently Malaysia and Singapore.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	Phenolic Surface Film – High-gsm Standard 165 gsm
	Back	Sanded core or Veneer
	Face Color	Dark Brown
	Back color	Natural Wood Color
	Wood Species	Acacia,Eucalyptus
	Core Grade	Mixed Grade
	Glue Type	WBP Melamine Eco
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	3

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	570
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 5000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	30 | 35 | 45 | 55
	Min Bending Strength (Across Grain) (Mpa)	15 | 20 | 25 | 30
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	FFP02002440122012 | FFP02002440122015 | FFP02002440122018 | FFP02002440122021 | FFP02002500125012 | FFP02002500125015 | FFP02002500125018 | FFP02002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



HDO PLYWOOD

HDO Plywood is coated with high density phenolic coating for maximum repetition and glossy concrete surface.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



HDO PREMIUM HD FORMPLY 2S - HDO PLYWOOD

SKU: HDO30HD


HDO Premium HD Formply 2S is the ultimate concrete forming plywood, featuring a double-sided premium HDO coating, high-density wood construction, and unmatched durability for maximum repetitions and exceptional performance.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm
	Alternative Dimensions	4.00×8.00×11/16 | 4.00×8.00×19/32
Materials	Face	HDO Premium High Density Coating
	Back	HDO Premium High Density Coating
	Face Color	Grey
	Back color	Grey
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20
Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Moisture Content (%)	12
	Density (kg/m3)	630
	Bonding Strength (Mpa)	1
	Thickness Swelling (%)	8

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

More

Brand Name	VINAWOOD
Model Number	HDO30HD08041116 | HDO30HD08041932
Place of Origin	Vietnam



HDO PREMIUM FORMPLY 2S - HDO PLYWOOD

SKU: HDO3000

HDO Premium Formply 2S is a revolutionary concrete forming plywood featuring a double-sided premium HDO coating for maximum repetitions, exceptional durability, and versatility.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm
	Thickness (mm)	15.00 | 18.00
	Alternative Dimensions	4.00×8.00×11/16 | 4.00×8.00×19/32
Materials	Face	HDO Premium Coating
	Back	HDO Premium Coating
	Face Color	Grey | Yellow
	Back color	Grey
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Phenolic

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20
Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	6000 | 7000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50
	Min Bending Strength (Across Grain) (Mpa)	25 | 30
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	HDO300008041116 | HDO300008041932
	Place of Origin	Vietnam



Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



HDO STANDARD HD FORMPLY 1SF - HDO PLYWOOD

SKU: HDO20HD


HDO Standard HD Formply 1SF is the ultimate concrete forming plywood, featuring high-density wood construction for unparalleled durability and a premium HDO coating for superior protection.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm
	Alternative Dimensions	4.00×8.00×11/16 | 4.00×8.00×19/32
Materials	Face	HDO Premium Coating
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Grey
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20
Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Moisture Content (%)	12
	Density (kg/m3)	630
	Bonding Strength (Mpa)	1
	Thickness Swelling (%)	8

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Brand Name	VINAWOOD
Model Number	HDO20HD08041116 | HDO20HD08041932
Place of Origin	Vietnam

More



HDO STANDARD FORMPLY 1SF - HDO PLYWOOD

SKU: HDO2000

HDO Standard Formply 1SF is a high-quality, durable plywood product that is ideal for concrete forming. It is made from a superior wood core that is coated with a premium HDO coating on one side and a phenolic backer on the other side. HDO Standard Formply 1SF can be reused many times without losing its shape or surface quality.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm
	Thickness (mm)	15.00 | 18.00
	Alternative Dimensions	4.00×8.00×11/16 | 4.00×8.00×19/32
Materials	Face	HDO Premium Coating
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Grey | Yellow
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Phenolic

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	20
Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	6000 | 7000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50
	Min Bending Strength (Across Grain) (Mpa)	25 | 30
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	HDO200008041116 | HDO200008041932
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



HDO BASIC FORMPLY 2S - HDO PLYWOOD

SKU: HDO1000

HDO Basic Formply 2S is our best selling HDO Formply. It is made from 100% Hardwood, WBP Glue, and HDO Basic Coating Surface. This plywood sheet is made and tested with rigorous procedures to ensure quality consistency.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm
	Thickness (mm)	15.00 | 18.00
	Alternative Dimensions	4.00×8.00×11/16 | 4.00×8.00×19/32
Materials	Face	HDO Basic Coating
	Back	HDO Basic Coating
	Face Color	Dark Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus
	Core Grade	AA Grade
	Glue Type	Exterior Basic Glue
Application	Application	Formwork
	Formaldehyde Emissions	E2
	Maximum Repetition (times)	10

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance

Width & Length Tolerances (mm)	1mm per 1 meter
Thickness Tolerance (mm)	According to EN315: +0.74 / -0.94
Moisture Content (%)	12
Density (kg/m3)	600
Bonding Strength (Mpa)	1
Mean Modulus of Elasticity (Along Grain) (Mpa)	6000 | 7000
Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000
Min Bending Strength (Along Grain) (Mpa)	40 | 50
Min Bending Strength (Across Grain) (Mpa)	25 | 30
Thickness Swelling (%)	8

More

Brand Name	VINAWOOD
Model Number	HDO100008041116 | HDO100008041932
Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



KS TEGO

KS Tego is coated phenolic panel made according to KSF 3101 Standard

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



KS 테고 프리미엄 (KS TEGO PREMIUM) - VINAWOOD 제품

SKU: N/A

KS 테고 프리미엄은 VINAWOOD에서 제작한, 100% 고밀도 경목과 AAA 등급을 사용하여 고품질의 필름 직면 합판을 제공하며, 고반복 콘크리트 주조에 이상적입니다. 이 제품은 WBP Phenolic T1 접착제와 E1 Formaldehyde 표준을 만족하며, 대한민국 표준 협회(KSA)의 KS 마크 인증을 받았습니다. VINAWOOD는 다년간의 품질 평판과 ISO9001, FSC, CE 마킹 등의 인증으로 고객의 믿음을 받고 있습니다.

Sizes	Dimensions (mm)	910×1820 mm | 1220×2440 mm
	Thickness (mm)	12
Materials	Wood Species	Acacia,Eucalyptus,Hevea
	Glue Type	WBP Phenolic

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



KS 테고 표준 (KS TEGO STANDARD) - VINAWOOD 제품

SKU: N/A

KS 테고 표준는 100% 고밀도 경목과 AAA 등급을 사용하여 고품질의 필름 직면 합판을 제공하며, 고반복 콘크리트 주조에 이상적입니다. 이 제품은 T1 접착제와 E1 Formaldehyde 표준을 만족하며, 대한민국 표준 협회(KSA)의 KS 마크 인증을 받았습니다. VINAWOOD는 다년간의 품질 평판과 ISO9001, FSC, CE 마킹 등의 인증으로 고객의 믿음을 받고 있습니다.

Sizes	Dimensions (mm)	910×1820 mm | 1220×2440 mm
	Thickness (mm)	12
Materials	Wood Species	Acacia,Eucalyptus,Hevea

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



KS 테고 에코 (KS TEGO ECO) - VINAWOOD 제품

SKU: N/A

KS 테고 에코는 고품질의 필름 직면 합판으로, 건설 현장의 콘크리트 형틀용으로 이상적입니다. 이 제품은 T1 접착제와 E1 Formaldehyde 표준을 만족하며, 대한민국 표준 협회(KSA)의 KS 마크 인증을 받았습니다. VINAWOOD는 다년간의 품질 평판과 ISO9001, FSC, CE 마킹 등의 인증으로 고객의 믿음을 받고 있습니다.

Sizes	Dimensions (mm)	910×1820 mm | 1220×2440 mm
	Thickness (mm)	12
Materials	Wood Species	Mixed Hardwood

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



LAMINATED VENEER LUMBER (LVL)

LVL is Laminated Veneer Lumber for a wide range of purposes such as packing, door frame, and furniture frame.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



LVL EXTRA

SKU: LVL01EX

LVL Extra is a type of Laminated Veneer Lumber for a wide range of purposes such as packing, door frame, and furniture frame. LVL Extra has F4* Glue and uses best hardwood veneer.

Sizes	Dimensions (mm)	1090×43 mm | 1108×43 mm | 2400×43 mm | 662×43 mm | 680×43 mm | Custom sizes
	Thickness (mm)	Custom Thicknesses
Materials	Face	Core Veneer
	Back	Core Veneer
	Face Color	Natural Wood Color
	Wood Species	Mixed Hardwood
	Core Grade	AA Grade
	Glue Type	MR Standard
Application	Application	Packing | Padding
	Formaldehyde Emissions	F4S
Technical Performance	Moisture Content (%)	12
	Density (kg/m3)	605

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



LVL BASIC

SKU: LVL01BS

LVL Basic is a type of Laminated Veneer Lumber for a wide range of purposes such as packing, door frame, and furniture frame.

Sizes	Dimensions (mm)	1090×43 mm | 1108×43 mm | 2400×43 mm | 662×43 mm | 680×43 mm | Custom sizes
	Thickness (mm)	Custom Thicknesses
Materials	Face	Core Veneer
	Back	Core Veneer
	Face Color	Natural Wood Color
	Wood Species	Mixed Tropical Wood
	Core Grade	Mixed Grade
	Glue Type	MR Standard
Application	Application	Packing | Padding
	Formaldehyde Emissions	E1 | E2
Technical Performance	Moisture Content (%)	15
	Density (kg/m3)	500

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MARINE PLYWOOD

Marine plywood can be used for many applications such as decking, ship interiors/exteriors, and container flooring.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MARINE EXTRA PLYWOOD

SKU: MP01EX

Marine Plywood is made of high quality veneer and Class 2 Melamine glue to achieve desired strength and durability characteristics. Marine plywood can be used for many applications such as decking, ship interiors/exteriors, and container flooring. Marine Extra Plywood is the high-density marine plywood line with 3 grades: A Stress, B Stress, and C Stress.

Sizes	Dimensions (mm)	1160×2400 mm | 634×2400 mm | Custom sizes
	Thickness (mm)	28 | Custom Thicknesses
Materials	Face	Keruing A
	Back	Keruing B
	Face Color	Natural Wood Color
	Wood Species	Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Melamine Top
Application	Application	Boat Building | Container Flooring | Docks | Flooring
	Formaldehyde Emissions	E2
Technical Performance	Moisture Content (%)	12
	Density (kg/m3)	745 | 795 | 845

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MARINE STANDARD PLYWOOD

SKU: MP01SD

Marine Plywood is made of high quality veneer and Class 2 Melamine glue to achieve desired strength and durability characteristics. Marine plywood can be used for many applications such as decking, ship interiors/exteriors, and container flooring. Marine Standard Plywood is the best seller of Vinawood Marine grade category.

Sizes	Dimensions (mm)	1160×2400 mm | 634×2400 mm | Custom sizes
	Thickness (mm)	28 | Custom Thicknesses
Materials	Face	Keruing A
	Back	Keruing B
	Face Color	Natural Wood Color
	Wood Species	Eucalyptus
	Core Grade	AA Grade
	Glue Type	WBP Melamine Top
Application	Application	Boat Building | Container Flooring | Docks | Flooring
	Formaldehyde Emissions	E2

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

	Thickness Tolerance (mm)	EN315
	Moisture Content (%)	12
	Density (kg/m3)	705
	Bonding Strength (Mpa)	1.0
Technical Performance	Mean Modulus of Elasticity (Along Grain) (Mpa)	7000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	6000
	Min Bending Strength (Along Grain) (Mpa)	70
	Min Bending Strength (Across Grain) (Mpa)	60
	Thickness Swelling (%)	8



Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MDO PLYWOOD

MDO is a special plywood made for strength and durability. It will give matte concrete surface and doesn't leave grain marks on concrete.

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MDO 1SF PANEL WITH FILM BACKER - HIGH DENSITY - PURPLE COLOR - MDO PLYWOOD

SKU: MDO3HDP

Introducing the MDO 1SF Panel with Film Backer - High Density - Purple Color by VINAWOOD, designed to meet the demands of heavy-duty formwork applications. This superior plywood features a high-density hardwood core made from Acacia, Eucalyptus, and Hevea wood species. The distinctive purple color MDO coating on one side and the top-grade 125gsm Phenolic Surface Film on the other provide enhanced durability and weather resistance. Experience unmatched strength, excellent moisture control, and a matte concrete surface without grain marks. Choose the MDO 1SF Panel with Film Backer - High Density - Purple Color for a robust and long-lasting construction solution.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
	Alternative Dimensions	xx
Materials	Face	MDO 325 gsm
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Kraft Paper Color Purple
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	17

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	630
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	5000 | 6000 | 7000 | 9000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 7000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 60 | 35
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	MDO3HDP2440122012 | MDO3HDP2440122015 | MDO3HDP2440122018 | MDO3HDP2440122021 | MDO3HDP2500125012 | MDO3HDP2500125015 | MDO3HDP2500125018 | MDO3HDP2500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MDO 1SF PANEL WITH FILM BACKER - MDO PLYWOOD

SKU: MDO3000

Discover the versatile and eco-friendly MDO 1SF Panel with Film Backer by VINAWOOD, perfect for formwork applications. This durable plywood offers a matte concrete surface, strong bonding and bending strength, moisture resistance, and an AA-grade core made from Acacia, Eucalyptus, and Hevea wood species. Choose MDO 1SF for a reliable and cost-effective construction solution.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	MDO 325 gsm
	Back	Phenolic Surface Film – Top grade 125 gsm
	Face Color	Kraft Paper Color Light Brown
	Back color	Dark Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	15

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	MDO30002440122012 | MDO30002440122015 | MDO30002440122018 | MDO30002440122021 | MDO30002500125012 | MDO30002500125015 | MDO30002500125018 | MDO30002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MDO 2S PANEL - MDO PLYWOOD

SKU: MDO2000

Introducing the versatile and high-performing MDO 2S Panel by VINAWOOD, specifically designed to cater to your diverse formwork application needs. This exceptional plywood panel combines the benefits of medium density overlay (MDO) with top-quality materials to deliver a premium solution for your construction projects.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	MDO 325 gsm
	Back	MDO 325 gsm
	Face Color	Kraft Paper Color Light Brown
	Back color	Kraft Paper Color Light Brown
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	25

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8

More	Brand Name	VINAWOOD
	Model Number	MDO20002440122012 | MDO20002440122015 | MDO20002440122018 | MDO20002440122021 | MDO20002500125012 | MDO20002500125015 | MDO20002500125018 | MDO20002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



MDO 1S PANEL - MDO PLYWOOD

SKU: MDO1000

Introducing the VINAWOOD MDO 1S Panel, a single-sided medium density overlay (MDO) coated plywood designed to cater to your formwork needs. This cost-effective solution combines the benefits of a smooth, matte concrete surface without grain marks while maintaining its natural wood appearance on the other side. With up to 15 repetitions, the MDO 1S Panel is an ideal choice for small to medium-sized construction projects, ensuring efficient use and a professional finish. Experience the quality and affordability of VINAWOOD's MDO 1S Panel in your construction projects today.

Sizes	Dimensions (mm)	2440.00 x 1220.00 mm | 2500.00 x 1250.00 mm
	Thickness (mm)	12.00 | 15.00 | 18.00 | 21.00
Materials	Face	MDO 325 gsm
	Back	Sanded core or Veneer
	Face Color	Kraft Paper Color Light Brown
	Back color	Natural Wood Color
	Wood Species	Acacia,Eucalyptus,Hevea
	Core Grade	AA Grade
	Glue Type	WBP Phenolic
Application	Application	Formwork
	Formaldehyde Emissions	E1
	Maximum Repetition (times)	15

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

Technical Performance	Width & Length Tolerances (mm)	1mm per 1 meter
	Thickness Tolerance (mm)	According to EN315: +0.56 / -0.76 | According to EN315: +0.65 / -0.85 | According to EN315: +0.74 / -0.94 | According to EN315: +0.83 / -1.03
	Moisture Content (%)	12
	Density (kg/m3)	600
	Bonding Strength (Mpa)	1
	Mean Modulus of Elasticity (Along Grain) (Mpa)	4000 | 6000 | 7000 | 8000
	Mean Modulus of Elasticity (Across Grain) (Mpa)	4000 | 5000 | 6000 | 3000
	Min Bending Strength (Along Grain) (Mpa)	40 | 50 | 30 | 55
	Min Bending Strength (Across Grain) (Mpa)	20 | 25 | 30 | 35
	Thickness Swelling (%)	8
More	Brand Name	VINAWOOD
	Model Number	MDO10002440122012 | MDO10002440122015 | MDO10002440122018 | MDO10002440122021 | MDO10002500125012 | MDO10002500125015 | MDO10002500125018 | MDO10002500125021
	Place of Origin	Vietnam

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



PRODUCT SAMPLE

Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com



HAND SAMPLES

SKU: SPL0100

At VINAWOOD, we understand the importance of experiencing our high-quality plywood products firsthand before making a decision. That's why we offer a convenient sample ordering service that allows you to explore our diverse range of film faced plywood and MDO panels with ease.

Sizes	Thickness (mm)	15 | 18
Sample Group	Sample Product Name	Form Basic | MDO 1S | MDO 1SF | MDO 1SF High Density – Purple | MDO 2S | Pro Form | Pro Form High Density | Top Form | Top Form Plus
	Sample Size	10×10 cm | 10×20 cm | 30×30 cm


Sales Office: +84-83333-2333
Email: plywood@vinawoodltd.com

VINAWOOD

#1 PLYWOOD SUPPLIER IN VIETNAM

PRODUCT E-CATALOG

PRODUCTION PROCESS



U.S.A. and Canada

Tel: +84-83-333-2337
na@vinawoodltd.com

Middle East & Africa

Tel: +84-83-333-2333
mea@vinawoodltd.com

Asia Pacific & All Others

Tel: +84-83-333-2333
ap@vinawoodltd.com

Quality Assurance

Tel: +84-83-333-2333
iaa@vinawoodltd.com